

05-01-2011

## Aluminium–Magnesium-Powder 35 – 325 mesh

<b>Composition:</b>	<b>Made from Al / Mg alloy</b> <b>50,0 % (+/- 2 %) Aluminium / 50,0 % Magnesium</b> <b>(+/-2%)</b>
<b>Granulometry:</b>	<b>Powder 35 – 325 mesh</b> <b>Sieve analysis: JEL 200</b> <b>Sieve inlet: DIN 4188</b>  <b>- 35 mesh (-500 my) 100 %</b> <b>- 325 mesh (-45 my) max. 15 %</b>
<b>Density:</b>	<b>d<sub>s,typ</sub> = 0.95-1.0 kg / dm<sup>3</sup></b>
<b>Special Characteristic:</b>	<b>if required passivated with 0,5 % oil</b>
<b>Packing:</b>	<b>UN certified steel drums with 210 l</b>

