

05-01-2011

Aluminium - Magnesium Powder AlMg 100/180

Application:

Pyrotechnic

Composition:

**Made from Al / Mg alloy
50,0 % (+/- 2 %) aluminium / 50,0 % magnesium (+/-2%)**

Granulation:

**AlMg powder 100/180
Typical sieve analyse to JEL 200
sieve inlet: DIN 4188**

> 180 µm	max. 5 %
100 - 180 µm	min. 85 %
< 100 µm	min. 10 %

Apparent Density:

900-1000 kg / m³

**Special
Properties:**

**Due to a special production procedure
a low oxide content is achieved**

Packing:

UN certified 216 l steel drums

