

05-01-2011

MAGNESIUM POWDER

MPF3

APPLICATION :	Pyrotechnic
COMPOSITION :	Made from Mg min.99.90%
GRANULATION :	Mg Powder 100/180 Typical sieve analyse to JEL 200 Sieve inlets : DIN 4188
	< 250 µm 100 % > 180 µm 6 % max. < 105 µm 12 % max.
APPARENT DENSITY :	0.40 gm/cm³ min.
SPECIAL PROPERTIES :	Due to a special production procedure low oxide content is achieved
PACKING :	UN-CERTIFIED 216-L STEEL DRUMS

