

05-01-2011

Magnesium Powder 0/100 my

Application:	Pyrotechnic
Composition:	Made from Mg min. 99,90 %
Granulation:	Mg powder 0/100 my Typical sieve analyse to JEL 200 sieve inlet: DIN 4188
	> 100 µm max.10 % > 63 µm 40-70 % < 63 µm min. 30 %
Apparent Density:	550-650 kg / m³
Special Properties:	Due to a special production procedure a low oxide content is achieved
Packing:	UN-CERTIFIED 216-L STEEL DRUMS

