

05-01-2011

Magnesium - Powder MgP 0/160

Application:	Pyrotechnic
Composition:	Made from Mg min. 99,90 %
Granulation:	Mg powder 0/160 Typical sieve analyse to JEL 200 sieve inlet: DIN 4188
	> 200 µm max. 5 % > 160 µm max.10 % < 160 µm min. 90 %
Apparent Density:	650-750 kg / m³
Special Properties:	Due to a special production procedure a low oxide content is achieved
Packing:	UN-CERTIFIED 216-L STEEL DRUMS

