

05-01-2011

Magnesium - Powder MgP 0/63

Application:	Pyrotechnic
Composition:	Made from Mg min. 99,90 %
Granulation:	Mg powder 0/63 Typical sieve analyse to JEL 200 sieve inlet: DIN 4188
	> 100 µm max. 0%
	> 63 µm max.10%
	< 63 µm min. 90%
Apparent Density:	550-600 kg / m³
Special Properties:	Due to a special production procedure a low oxide content is achieved
Packing:	UN-CERTIFIED 216-L STEEL DRUMS

