

05-01-2011

Magnesium - Powder MgP 28/100mesh

Application:	Pyrotechnic								
Composition:	Made from Mg min. 99,90 %								
Granulation:	Mg powder 28/100 mesh Typical sieve analyse to JEL 200 sieve inlet: DIN 4188 <table><tr><td>> 28 mesh</td><td>max. 5 %</td></tr><tr><td>> 35 mesh</td><td>30-50 %</td></tr><tr><td>> 100 mesh</td><td>min. 95 %</td></tr><tr><td>< 150 µm</td><td>max. 5 %</td></tr></table>	> 28 mesh	max. 5 %	> 35 mesh	30-50 %	> 100 mesh	min. 95 %	< 150 µm	max. 5 %
> 28 mesh	max. 5 %								
> 35 mesh	30-50 %								
> 100 mesh	min. 95 %								
< 150 µm	max. 5 %								
Apparent Density:	750-850 kg / m³								
Special Properties:	Due to a special production procedure a low oxide content is achieved								
Packing:	UN-certified 210-l steel drums								

