

05-01-2011

Magnesium - Powder MgP 63/180 passivated

Application:	Pyrotechnic						
Composition:	Made from Mg min. 99,90 %, passivated with Stearin Fe and Mn <0.1 %						
Granulation:	Mg powder 63/180 Typical sieve analyse to JEL 200 sieve inlet: DIN 4188 <table><tr><td>> 180 µm</td><td>0 %</td></tr><tr><td>> 90 µm</td><td>40-85 %</td></tr><tr><td>> 63 µm</td><td>80-100 %</td></tr></table>	> 180 µm	0 %	> 90 µm	40-85 %	> 63 µm	80-100 %
> 180 µm	0 %						
> 90 µm	40-85 %						
> 63 µm	80-100 %						
Apparent Density:	650-750 kg / m³						
Special Properties:	Due to a special production procedure a low oxide content is achieved						
Packing:	UN-CERTIFIED 216-L STEEL DRUMS						

