

05-01-2011

Magnesium Rasplings MGS - 80 M

Application: Metallorganic Compounds
Grignard Reaction

Size: Thick: ~ 0.8 mm
Wide: ~ 1.5 mm
Long: ~ 5- 10 mm

Composition: Cu 0.02 % max., Fe 0.05 % max.,
Mn 0.01 % max., Ni 0.001 % max.,
Sn 0.01 % max., Pb 0.01 % max.,
total others 0.05 % max.,
Mg 99.90 % min.

Special Properties: The material is dustfree, has a regular shape
and batches will be uniform.
If required, this product can be delivered
made from high purity Magnesium

Packing: UN certified 216 l steel drums or big bags

