

05-01-2011

MG 66 Injection Blend

Application:	Hot metal desulfurization. For mono-injection and co-injection with calcium carbide or lime.										
Composition:	Min. 66 % magnesium made of 99,9 % metallic Mg; approx. 10 % Al; rest Al₂O₃ and lime										
Granulation:	<table><tr><td>> 1.0 mm</td><td>0 %</td></tr><tr><td>> 0.8 mm</td><td>max 5 %</td></tr><tr><td>0.5 - 0.8 mm</td><td>35 - 60 %</td></tr><tr><td>0.2 - 0.5 mm</td><td>35 - 60 %</td></tr><tr><td>< 0.2 mm</td><td>traces</td></tr></table>	> 1.0 mm	0 %	> 0.8 mm	max 5 %	0.5 - 0.8 mm	35 - 60 %	0.2 - 0.5 mm	35 - 60 %	< 0.2 mm	traces
> 1.0 mm	0 %										
> 0.8 mm	max 5 %										
0.5 - 0.8 mm	35 - 60 %										
0.2 - 0.5 mm	35 - 60 %										
< 0.2 mm	traces										
Bulk Density:	approx. 850 kg/m³										
Special Properties:	Very good flowability, enabling exact dosage into the ladle. A special coating prevents oxidation, decreases the hazard of dust explosions and substantially increases storage life.										
Packing:	Container, Silo - Truck, Big Bag										

