

05-01-2011

## MG 90 A Injection Blend

<b>Application:</b>	<b>Hot metal desulfurization. For monoinjection and coinjection with calcium carbide or lime.</b>										
<b>Composition:</b>	<b>min. 90 % Mg- Al-alloy 8 % lime 2 % cryolithe</b>										
<b>Granulation:</b>	<table><tr><td><b>&gt; 1.0 mm</b></td><td><b>0 %</b></td></tr><tr><td><b>&gt; 0.8 mm</b></td><td><b>max 5 %</b></td></tr><tr><td><b>0.5 - 0.8 mm</b></td><td><b>35 - 60 %</b></td></tr><tr><td><b>0.2 - 0.5 mm</b></td><td><b>35 - 60 %</b></td></tr><tr><td><b>&lt; 0.2 mm</b></td><td><b>traces</b></td></tr></table>	<b>&gt; 1.0 mm</b>	<b>0 %</b>	<b>&gt; 0.8 mm</b>	<b>max 5 %</b>	<b>0.5 - 0.8 mm</b>	<b>35 - 60 %</b>	<b>0.2 - 0.5 mm</b>	<b>35 - 60 %</b>	<b>&lt; 0.2 mm</b>	<b>traces</b>
<b>&gt; 1.0 mm</b>	<b>0 %</b>										
<b>&gt; 0.8 mm</b>	<b>max 5 %</b>										
<b>0.5 - 0.8 mm</b>	<b>35 - 60 %</b>										
<b>0.2 - 0.5 mm</b>	<b>35 - 60 %</b>										
<b>&lt; 0.2 mm</b>	<b>traces</b>										
<b>Bulk Density:</b>	<b>approx. 850 kg/m<sup>3</sup></b>										
<b>Special Properties:</b>	<b>Very good flowability, enabling exact dosage into the ladle. A special coating prevents oxydation, decreases the hazard of dust explosions and substantially increases storage life.</b>										
<b>Packing:</b>	<b>Flobin, Silo - Truck, Big Bag</b>										

